

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 15/58, A61F 13/02, C09J 133/08, 157/00, 175/04	A2	(11) International Publication Number: WO 97/06836	(43) International Publication Date: 27 February 1997 (27.02.97)
---	----	--	--

(21) International Application Number: PCT/GB96/01954

(22) International Filing Date: 12 August 1996 (12.08.96)

(30) Priority Data:

9516487.7	11 August 1995 (11.08.95)	GB
9522938.1	9 November 1995 (09.11.95)	GB
9615125.3	18 July 1996 (18.07.96)	GB
9615127.9	18 July 1996 (18.07.96)	GB

(71) Applicant (for all designated States except US): SMITH & NEPHEW PLC [GB/GB]; 2 Temple Place, Victoria Embankment, London WC2R 3BP (GB).

(72) Inventor; and

(75) Inventor/Applicant (for US only): WEBSTER, Iain [GB/GB]; 38 Wydale Road, Osbaldwick, York YO1 3PG (GB).

(74) Agent: SMITH & NEPHEW GROUP RESEARCH CENTRE; Corporate Patents & Trademarks Dept., York Science Park, Heslington, York YO1 5DF (GB).

(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).


Published

Without international search report and to be republished upon receipt of that report.

(54) Title: ADHESIVES

(57) Abstract

There are described novel adhesives which are capable of being "switched" from a tacky to a non-tacky state. Such switchable adhesives are especially advantageous when used in medical dressings, and therefore novel medical dressings comprising a switchable adhesive layer, a removable light occlusive layer and an intermediate transparent or translucent layer are also described.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

ADHESIVES

The present invention relates to adhesives, to methods for producing adhesives and to articles comprising adhesives. In particular this invention relates to 'switchable' adhesives, that is, adhesives which may be influenced to change from a tacky to a non-tacky state thereby reducing the peel strength of the adhesive.

Adhesive products such as adhesive surgical or medical dressings and bandages normally comprise a layer of a pressure sensitive adhesive. However, when conventional adhesive dressings and/or bandages are removed they often cause localised trauma to the patient.

There has therefore long been a desire to provide, for example, adhesive dressings which can exhibit a reduction in peel strength of the adhesive, and therefore cause less localised trauma, than conventional adhesives when the dressing is removed. Hereinafter, adhesives which can be changed from a tacky to a non-tacky state will be referred to as 'switchable adhesives'.

Switchable adhesives are known. For example, US Patents Nos. 5032637, 5352516, 4331576 and 5182323 describe adhesives which become less tacky, ie. are switchable, in contact with water. However, such adhesives are unsuitable, for example, if used on a wound dressing and the patient's wound needs to be kept dry. UV switchable adhesives are described in US Patents Nos. 4286047, 4968559 and 5118567 and Japanese Patent No. 3043988. Such adhesives suffer from the disadvantage that they may require high doses of UV radiation or may need to be used in conjunction with photoinitiators which result in undesirable bi-products. Since it remains undesirable to expose patients to too much ultra violet radiation, there remains a need for a switchable adhesive which can undergo a reduction in peel strength at low dosages of UV radiation or more preferably by exposure to visible light irradiation and/or which removes or mitigates the need for the use of photoinitiators.

We have now surprisingly found an adhesive which is switchable when exposed to, inter alia, visible light, ie. is visible light switchable, or low dosages of UV light. Such visible light switchable or low dosage UV light switchable adhesives generally comprise an
5 adhesive polymeric group with bound-in polymerisable or curable group.

Thus according to the invention we provide a switchable adhesive composition comprising an adhesive polymeric moiety and
10 a plurality of bound-in curable moieties.

The bound-in curable moieties are preferably photocurable moieties. By the term curable moieties we mean moieties which are capable of undergoing a reaction, eg. photo curing to produce a
15 polymer comprising the adhesive polymeric group, which polymer has greatly increased molecular weight. The preferred curable moieties are those which produce a polymer of increased molecular weight by way of cross-linking the adhesive polymeric moiety.

20 The bound-in curable moiety may be introduced into the adhesive polymeric moiety by forming a polymer comprising the adhesive polymeric moiety and the bound-in curable moiety, eg. the curable moiety is chemically bound to the adhesive polymeric moiety.

25 The adhesive polymeric moiety will generally comprise a polymeric 'backbone'. Any conventionally known adhesive polymers may be used provided that such polymers are, where desirable, reactable to produce adducts with curable moieties such that the
30 curable moieties are bound-in.

Preferred adhesive polymeric moieties include polyurethanes, polyacrylates and free radical polymerisable vinyl moieties. Polyacrylates are especially preferred.

35 When the adhesive polymeric moiety comprises a polyurethane adhesive it may be a lightly cross-linked or linear polyurethane adhesive. When the adhesive polymeric moiety is a

polyurethane the bound-in curable groups may form end groups on the polyurethane backbone, may be incorporated into the polymer backbone or may be pendant groups, eg. along the backbone.

- 5 Desirably the bound-in curable groups in the polyurethane adhesives are located at or close to free ends of the backbone and curing causes these ends to become linked together.

- 10 Particularly preferred adhesives are acrylates. By the term acrylate adhesives we include acrylates, methacrylates and acrylate copolymer adhesives. Indeed acrylate copolymer adhesives are especially preferred, eg. alkyl acrylate copolymers. The 'backbone' polymer may be a copolymer with one or more acrylates. Alternatively the 'backbone' polymer may be a copolymer with one
15 or more acrylates and a free radical polymerisable vinyl moiety. Such vinyl moieties include compounds such as itaconic anhydride, maleic anhydride or vinyl azlactone or glycidyl methacrylate. Especially preferred acrylate adhesives are those wherein the polymeric 'backbone' includes a proportion of unreacted carboxylic
20 acid residues, eg. acrylic acid residues. Unreacted acid residues are particularly advantageous since they may be derivatised, eg. esterified, with curable groups. Thus especially preferred acrylate copolymers are acrylate tricopolymers. A particularly preferred adhesive moiety is an alkyl acrylate/alkyl acrylate/acrylic acid tri-
25 copolymer. An especially preferred adhesive moiety is an n-butyl acrylate/2-ethylhexyl acrylate/acrylic acid tri-copolymer. The most preferred tri-copolymer is n-butyl acrylate/2-ethylhexyl acrylate/acrylic acid in the ratios 47/47/6. Such an adhesive composition is hereinafter referred to as A8 adhesive.

30

- Any conventionally known unsaturated compounds, eg. olefinic or aromatic compounds, may be used as the bound-in curable moiety provided that they are able to react with the polymeric 'backbone'. Free radical curable moieties are preferred, such
35 groups include acrylates and methacrylates which may form, for example, esters or amides with any unreacted acid groups in the polymeric 'backbone'. Curable groups which are photodimerisable may also be used and include groups such as anthracenes,

cinnamates, maleimides and coumarin groups. Mixtures of all of the aforesaid may also be used. Preferred bound-in curable groups are selected from acrylates, methacrylates and anthracenes. Especially preferred bound-in curable groups are free radical curable groups such as acrylates and/or methacrylates. Most preferred are methacrylates such as hydroxyalkyl methacrylates wherein the hydroxyalkyl group possesses from 1 to 6 carbon atoms, eg. 1 to 4 carbon atoms and especially 1 or 2 carbon atoms. Especially preferred is hydroxyethylmethacrylate.

Alternatively, when the polymeric 'backbone' comprises an acrylate moiety then the bound-in curable moiety may be a free radical polymerisable vinyl moiety as hereinbefore described.

The amount of the bound-in curable moiety present in the switchable adhesive composition may vary, depending, inter alia, upon the amount of tackiness desired in the switchable adhesive when it is switched from its tacky to its non-tacky state. Thus, the amount of the bound-in curable moiety, eg. hydroxyethyl methacrylate, present in the switchable adhesive composition may be from 0.4 to 50% by weight of polymer backbone preferably from 0.4 to 40% by weight and more preferably from 0.4 to 20% by weight. The free radical curable moieties are preferably present as from 0.4 to 5% by weight. The photodimerisable moieties are preferably present as from 10 to 15% by weight, eg. 13% by weight.

The switchable adhesive compositions of the invention may also include a free radical initiator. Any conventionally known free radical initiators may be used. Particularly preferred are those initiators which react to visible light radiation, although initiators which react under longer or shorter wavelength light may be used in compositions of the invention. Thus, free radical initiators which may be mentioned include titanocene photoinitiators; dye/co-initiator systems, eg. thionine/triethanolamine; dye/borate salt systems; dye/peroxide systems and 1,2-diketone/co-initiator systems, eg. camphorquinone/tertiary amine. Preferred free radical initiators are the titanocene initiators such as bis(γ^5 -cyclopentadienyl) bis [2,6-difluoro-3-(1H-pyrr-1-yl) phenyl]-titanium, sold as Irgacure 784

5

(Trade Mark) in the UK by Ciba Geigy. Initiators which react with UV light may be used, such initiators include the Irgacures. Such as Irgacure 651 (benzyl dimethyl ketal) or Irgacure 907 (2-methyl-1-[4-(methylthio)phenyl]-2-morpholino-propan-1-one); or the Uvatones, such as Uvatone 8302 (2,2-diethoxy-1,2-diphenyl ethanone).

The switchable adhesives of the invention which have a free radical bound-in curable group are preferably provided with a photoinitiator.

10

According to a further feature of the invention we provide a process for the manufacture of an adhesive composition as hereinbefore described which comprises reacting a polymeric 'backbone' as hereinbefore described with a curable moiety.

15

In particular we provide a process for the manufacture of an acrylate switchable adhesive composition as hereinbefore described which comprises reacting an unreacted carboxylic acid containing copolymer backbone with a curable, eg. photocurable, moiety to produce an adhesive composition comprising backbone polymer with bound-in curable groups as acid derivatives. The bound-in curable groups may be end groups, pendant groups or may be incorporated into the backbone.

20

The polyurethane adhesives of the invention may be manufactured by reacting the polyurethane with a free radical curable moiety. When the polyurethane adhesive is a linear polyurethane the bound-in curable groups may comprise any of the groups hereinbefore described, eg. acrylates or anthracenes. When the polyurethane adhesive is a cross-linked adhesive the bound-in curable group may vary depending upon the nature of the cross-linking group used in the polyurethane adhesive. For example if the polyurethane cross-linking group is a multifunctional alcohol any bound-in curable group may be used, eg. acrylates or anthracenes. Alternatively if the polyurethane cross-linking group is an acrylate or methacrylate then the bound-in curable group will preferably be a photodimerisable group, eg. anthracene. When the cross-linked polyurethane adhesive comprises an acrylate or

25

30

35

methacrylate cross-linking group then the cross-linking group is preferably thermally initiated. Such thermally initiated compositions may also include a thermal free radical initiator.

5 Suitable polyurethanes for use in the switchable adhesive composition can be derived from a polyester diol or preferably a polyether diol and a di-isocyanate. Suitable polyether diols include polyoxyalkylene diols in which the alkylene contains 2 to 4 carbon atoms such as polyoxyethylene, polyoxypropylene and
10 polyoxytetramethylene diols and mixtures thereof. Such polyether diols can suitably have an average molecular weight of 1000 to 8000 and preferably have a molecular weight of 1500 to 6000. A favoured polyether diol for forming the polyurethanes used in the invention is polyoxypropylene diol. An apt diol of this type is known
15 as PPG 2025, available from British Drug House, which has an average molecular weight of 2025. Another suitably hydrophilic group containing diol is a block copolymer of polypropylene glycol and ethylene oxide marketed as Dowfax 63N10 (Trade Mark) available from Dow Chemicals Inc.

20

Polyoxyalkylene diol residues can be used to render the adhesive formed therefrom moisture vapour transmitting.

Diisocyanates used to form the polyurethane can suitably have
25 an isocyanate functionality of 1.6 to 2.05 and can preferably have an isocyanate functionality of 2.0. Suitable diisocyanates include a aliphatic (including alicyclic) and aromatic diisocyanates. Favoured diisocyanates include toluene diisocyanate, 4,4'-diphenylmethane diisocyanate and 4,4'-dicyclo hexyl methyl diisocyanate which is the
30 preferred diisocyanate and which in an apt form is known as Desmodur W (Trade Mark) available from Bayer.

The polyurethane can optionally include a chain extending agent. Suitable chain extending agents include diols such as
35 ethane diol and butane diol, diamines for example ethylene diamine, and water. The molar ratio of diol or diol and diamine residues to diisocyanate residues in the polyurethane can suitably be 0.6 to 0.8:1 and preferably 0.65 to 0.75:1 for example 0.7:1.

When an isocyanate-terminated polyurethane has been prepared it can then be reacted with one or more hydroxyl group containing compounds which react with the isocyanate groups.

- 5 Preferably some of these compounds are mono-alcohols (although they may be other compounds which have a monofunctional group reacting with an isocyanate group, eg. mono-amines). One type of mono-alcohol may comprise the radiation curing group. Desirably such mono-alcohols are used to react with from 40 to 90% of the
- 10 isocyanate residues of the polymer, eg. from 55 to 70%. Particularly suitable mono-ols for use with polyurethane adhesive compositions include anthracene methanol, cinnamyl alcohol and hydroxy maleimides, since these comprise groups which cure, eg. photodimerise, under the influence of UV or visible light. In some
- 15 cases the dimerisation may be reversed on heating. Derivatives of such groups which are also curable may also be used. Thus the groups may be optionally substituted with substituents which do not substantially reduce curing.

- 20 Other mono-alcohols may be present in the polyurethane adhesives which comprise the cross-linking groups. Aptly, these include compounds having groups which can react with free-radicals, eg. unsaturated compounds which may be esters of acrylic or methacrylic acid in which there is at least one hydroxyl functional
- 25 group which is capable of reacting with an isocyanate group.

- The proportion of hydroxyl-containing compound which also contains an unsaturated functionality (if present) is desirably such as to react with from 15 to 25% of the free isocyanate groups in the
- 30 polyurethane. The remainder of the free isocyanate groups can react with the other hydroxyl group containing compounds which are present as chain terminators.

- In addition to the mono-alcohols discussed above, mono-ols
- 35 which are tackifying agents can be used to react with free isocyanate groups of the polyurethane. Such mono-alcohols include hydrogenated mono hydroxy tackifying resins, eg. hydrogenated abietyl alcohol.

A hydrophilic polyurethane can be formed by suitable choice of polyether diol. The polyurethane when hydrated may contain from 35 to 95% by weight of water, aptly 50 to 92%, preferably 70 to 90% and more preferably 75 to 85% by weight of water. Water absorption can be obtained by taking a known weight of the polyurethane and immersing in water for 24 hours. The hydrated polymer is removed from the water, excess water is removed by lightly blotting with absorbent paper and then the hydrated polyurethane is weighed. The water absorption of the polyurethane (% by weight) can then be calculated as (weight of hydrated polyurethane-weight of dry polyurethane) x 100/weight of hydrated polyurethane.

The curing reaction reacts the bound-in curable groups resulting in increased molecular weight of the adhesive polymer which may be initiated by visible light or longer or shorter wavelength light such as infra red or ultra violet light. Whilst it is preferable that the bound-in curable moiety reacts via a free radical reaction, it is most desirable that the reaction of the curable groups is visible light initiated. Thus the wavelength of the light used may be less than 700nm, eg. preferably between 400 and 700nm.

The dosage of light used may vary depending upon the switchable adhesive composition but is generally greater than 0.4 mW cm⁻² when UV light is used. When a visible light switchable adhesive is used ambient light may be used and therefore the dosage may vary.

The adhesive compositions of the invention may also be blended with a conventional adhesive composition to produce an adhesive mixture which is itself switchable. It is a further feature of the present invention to provide a switchable adhesive as hereinbefore described in admixture with an adhesive composition.

By the term adhesive composition we mean a composition comprising conventional adhesives known per se, such conventional adhesives are non-switchable adhesives.

Thus according to the invention we provide a switchable adhesive composition comprising an adhesive polymeric moiety and a visible light curable moiety.

5

The adhesives of the invention are preferably pressure sensitive adhesives (PSAs) and are particularly advantageous in the manufacture of adhesive tapes and adhesive dressings. By the term dressings we include wound dressings, adhesive bandages and adhesive tapes for medical use. The adhesives may also be useful in the manufacture of other conventional products which require a peelable adhesive, eg. masking tapes, stencils, etc.

10

Thus according to the invention we provide the use of a composition as hereinbefore described in the manufacture of an adhesive dressing.

15

Dressings comprising adhesive compositions of the invention are also themselves novel.

20

Thus according to a further feature of the invention we provide an adhesive dressing comprising a backing layer substantially coated on at least one surface thereof with an adhesive as hereinbefore described.

25

The adhesive coating may be a continuous coating on non-continuous, eg. may be a pattern spread adhesive.

The backing layer preferably comprises a light occlusive layer and a transparent or translucent layer. By the term light occlusive we particularly mean that the material is occlusive over the wavelength range that the photoinitiator absorbs in. Thus we especially prefer a light occlusive layer which is visible light occlusive. The light occlusive and transparent layers may be laminated together or alternatively the light occlusive layer may have a low peel strength adhesive on it's transparent layer facing surface.

30

35

Thus in use an adhesive dressing of the invention may be applied to the skin of a patient. When it is desired to remove or replace the dressing the light occlusive layer may be removed. The adhesive on the skin facing surface of the transparent layer can
5 then be exposed to either visible light or a light source and after a given time the peel strength of the adhesive will be reduced allowing the transparent layer to be removed from the patient's skin.

Thus according to the invention we provide a dressing as
10 hereinbefore described comprising a backing layer and an adhesive layer, wherein the backing layer comprises a removable light occlusive layer and a transparent layer intermediate the occlusive layer and the adhesive layer and wherein the adhesive layer comprises a switchable adhesive as hereinbefore described.

15 Any conventionally known occlusive and transparent materials may be used in the backing layer of the dressings of the invention. Preferred dressings are those which comprise a film, ie. thin film, backing layer, ie. both the occlusive and transparent layers
20 comprise a film, although other backing layers, eg. fabric layers, may also be considered appropriate.

The dressings of the invention may be manufactured using conventional methods known per se.

25 The occlusive layer of the backing layer may be adhesively bonded to the transparent layer or may be laminated thereto. If adhesively bonded then the peel strength of the bonding adhesive must be less than that of the switchable adhesive in its tacky form.

30 The dressings of the invention are especially useful in the treatment of wounds. Thus according to a further feature of the invention we provide a method of treating a wound on a patient which comprises applying a dressing as hereinbefore described to
35 the wound of a patient. The method may also include the removal of the dressing by removing the light occlusive layer of the dressing and then irradiating the adhesive through the transparent or translucent layer to render the adhesive non-tacky.

Many medicinal agents may be incorporated into the adhesive compositions of the present invention. By medicinal agent is meant pharmacologically active agents including agents which are topical anaesthetics such as xylocaine, bacteriostatic agents such as silver nitrate; anti-bacterial agents of which preferred forms are silver sulphadiazine and chlorhexidine salts; antibiotics; topical steroids, enzymes; tissue stimulants; coagulants and anticoagulants and antifungal agents. Other agents such as emollients may also be added.

The invention will now be illustrated with reference to the accompanying drawings and Examples.

Figure 1 is a cross-section of a dressing of the invention.

Figure 2 is a cross-section of a further dressing embodiment of the invention.

With reference to Figure 1, a dressing (1) comprises a backing layer (2) and an adhesive layer (3). The backing layer (2) comprises an occlusive layer (4) and a transparent layer (5) intermediate the occlusive layer (4) and the adhesive layer (3). The dressing may optionally be provided with appropriate carrier layers and protector layers.

In use the dressing (1) is adhered to the skin of a patient when the adhesive layer (3) is in a tacky form. When it is desired to remove the dressing (1) from the patient, the occlusive layer (4) is removed exposing the transparent layer (5) and thereby the adhesive layer (3) to visible light. The visible light causes the photoinitiator to initiate the free-radical cross-linking of the PSA through the pendant acrylate groups resulting in the adhesive losing its tackiness and peel strength. The time required for this reaction to be complete may vary, eg. from 1 to 15 minutes. The dressing may then be removed with reduced trauma to the patient.

The present invention will now be described by way of example only, with reference to the accompanying drawing, wherein Figure 2 illustrates schematically in cross-section a medical dressing according to the present invention when in use on patient.

5

Referring now to Figure 2, a medical dressing (10) is shown attached to a patient's skin (20). The dressing (10) comprises a wound facing absorbent layer (30) which is underneath a protective backing layer (40) at opposed edges (50, 60) the backing layer (40) is provided with adhesive (70) comprises groups which can be cross-linked under the influence of UV or visible light.

The backing layer (40) is provided with a cover (80) which is releasably secured to the backing layer (40) by a weak adhesive (90). Alternatively the cover (80) may be laminated to the backing layer (40). For ease of removal the cover (80) overlaps the backing layer (40) at its edges (100, 110).

When it is desired to remove the dressing from the skin of a patient, the cover (80) can be gripped at its edges (100, 110) and peeled off the backing layer (40) so as to expose the adhesive (70) to UV or visible light irradiation. This irradiation acts so as to cure the adhesive which, after a certain time (depending upon the adhesive used), causes the adhesive (70) to lose its tackiness to such an extent so that the dressing can be removed without causing trauma to the patient.

In order that the removal of the cover (80) does not itself cause trauma to the patient, the peel strength of the adhesive (90) adhering the cover (80) to the backing layer (40) should be substantially less than that of the adhesive (70) adhering the dressing (10) to the patient's skin.

Since the adhesive (70) loses tackiness on exposure to UV or visible light, it is desirable that the adhesive (70) is not exposed to the light for a substantial period when the dressing (10) is applied to a patient. Thus the adhesive (70) may be initially provided on the surface with release paper (not shown) which is opaque to UV and

13

visible light and which can be readily removed from the adhesive so that the dressing is ready for use.

The preparation and testing of adhesives suitable for use as the adhesive layer (70) will now be described in the following Examples.

The following Trade Marks are referred to herein:

10	<u>Trade Mark</u>	<u>Chemical/Apparatus</u>	<u>Company</u>
	Desmodur W	4,4-Dicyclohexylmethane diisocyanate	Bayer UK Ltd
	Metatin 812ES	Diocetyl tin dilaurate	Acima Chemical Industries Ltd Inc
15	Abitol	Hydroabietyl Alcohol	Hercules Inc
	Melinex	Grade 542 polyethyleneterephthalate	ICI Films
	AIBN	-Azo-iso-butyronitrile	Fisons
20	Irgacure 651	Benzildimethyl ketal	Ciba-Geigy
	Irgacure 784	Bis(γ^5 -cyclopentadienyl) bis[2,6-difluoro-3- (1,4-pyrr-1-yl) phenyl]- titanium	Ciba-Geigy
	Michler's Ketone	4,4'-Bis(dimethylamino)- benzophenone	Aldrich
25	Uvahand 250	UV Lamp	Dr Hönle

Example 1

Preparation of Acrylate/HEMA Switchable Adhesive

30

Weight of A8 Adhesive solution = 97.02g (32% solids) (equivalent to 0.0259 mols of acrylic acid).

Weight of 1,1'-Carbonyldiimidazole = 4.19g (0.0259 mols)

35

Weight of 1,8-Diazabicyclo[5,4,0]undec-7-ene (DBU) = 3.93g (0.0259 mols)

Weight of Hydroxyethyl Methacrylate (HEMA) = 3.36g (0.0259 mols)

A stirred solution of A8 adhesive in acetone was bubbled through with nitrogen for approx 30 minutes before the carbonyldiimidazole was added. The nitrogen bleed was then removed and a bubbler was attached to the round-bottom flask to monitor the production of carbon dioxide. This was left for approx 3 hours at 45°C. The HEMA and DBU were added to the adhesive solution at 45°C and left to stir for 3 hours. The sample was then left to stand for two days at room temperature to give a pale orange solution. The esterified solution was then added to diethyl ether and washed with 80ml of a 10% aqueous hydrochloric acid solution. After separation the switchable adhesive solution was washed with 80ml water and left to separate. The switchable adhesive solution was washed with 80ml of a 10% aqueous potassium hydrogen carbonate solution and left to separate. The separated diethyl ether solution of switchable adhesive was dried over anhydrous sodium sulphate and then filtered.

Example 2

Preparations of Switchable PSAs with Irgacure 784

Photoinitiator

Samples of Acrylate/HEMA switchable adhesives were prepared by mixing Irgacure 784 photoinitiator with the product of Example 1.

a) Adhesive of Example 1 = 42.1318g
Weight of solid = 5.9406g
Weight of Irgacure 784 = $0.5741 - 0.0020 = 0.572g$
= 9.61%

b) Adhesive of Example 1* = 40.6247g
Weight of solid = 4.9968g
Weight of Irgacure 784 = 0.5020g
= 10.0%

*Adhesive prepared as in Example 1, washed in dichloromethane rather than diethyl ether.

15

Adhesive solution 'a' was spread with a 0.030 inch spreading block onto Melinex and dried in a darkened fume cupboard. Peel strength testing was carried out from HDPE film and irradiation from a halogen lamp. The adhesive solution 'b' was spread with a 0.024
5 inch spreading block.

The two adhesive spreads were irradiated under a halogen lamp for switching for the peel strength studies. Irradiation time was 15 mins.

10

Example 3

Peel Strength Tests

The formulation of Example 2a) contained 9.6% Irgacure 784 and that of 2b) contained 10% Irgacure 784 photoinitiator. Samples were spread at about 30gm⁻² onto Melinex film. The samples were spread in an enclosed fume cupboard (darkened) and kept in a blacked out environment.

Adhesion to HDPE film, was based on the test described in the British Pharmacopoeia (1988), Appendix XX, method H - adhesives test 2., except that: Peeling was after 30 minutes. The specimens were cut and laminated to the HDPE film coated steel plates in the dark, under a red safelight and either were kept in the dark until
25 peeling or were exposed to a halogen type light for half of the 30 minute dwell, after 10 minutes build up, (and allowed to cool for the last 5 minutes). Samples were transported and kept in light proof boxes until actual peeling.

30 Peel strength results are shown in Table I.

Table I

Peel Strength (Nm ⁻¹) from HDPE Film			
Example	Irgacure Content	Unirradiated	After Light Radiation
2a)	9.6%	32	6
2b)	10%	63	6

Example 4Preparation of Polyurethane Adhesives

5 1.32g of polyethylene glycol (PEG) 600 was placed in an oven
at 90°C for 15 mins to aid handling. 23.31g of polypropylene glycol
(PPG) 2025, the melted PEG 600, 0.37g of ethanediol (EDO) and
13.32g of Desmodur W were added to a 250ml flange flask. The
10 flask was placed in a water bath at 90°C and the contents stirred to
achieve a homogeneous mixture. This having been achieved, 0.1g
of Metatin 812ES was added and 50ml of carbon tetrachloride was
added as a solvent. The mixture was stirred for a further hour at
90°C to give a prepolymer composition. Meanwhile, 4.64g of Abitol
15 was placed in the oven at 60°C for 15 mins, 0.01g 4-methoxyphenol
was dissolved in 0.58g of 2-hydroxyethyl methacrylate and 6.47g of
9-anthracene methanol was mobilised with 30ml carbon
tetrachloride.

20 The 2-HEMA solution was then added to the prepolymer
composition, followed by the 9-anthracene methanol washed
through with further amounts of carbon tetrachloride (~10ml) and
stirring was then continued for a further 30 mins.

25 The Abitol was then added and the reaction mixture stirred in a
water bath (90°) for 30 mins.

30 The resultant switchable adhesive solution was then left
overnight to cool and was found to be a golden liquid of apparently
low viscosity (approximately 20% solids content).

Example 5Preparation of Films

35 The solution of Example 4 was used to produce four films.

a) Film 5a)

14.70g of the solution of Example 4 (corresponding to 3.0g of
solids) was mixed with 1% w/w relative to the solids content of the

17

solution, of AIBN and of Irgacure 651. Thus 0.03g of AIBN and of Irgacure 651 were added to the switchable adhesive solution and were stirred until well mixed.

- 5 The solution was then spread to a depth of 0.010 inches thickness on Melinex and left to dry overnight at room temperature in the dark.

- The dried 5a) film was thermally cured in an oven at 80°C for 4
10 minutes. The film was laminated to release paper by applying light finger pressure and stored in a dark cupboard for further use. Lamination was to the embossed side of the polyethylene sheet. The laminate was then cut into strips. The strips were then placed for varying periods under a Uvahand R50 UV irradiation source,
15 ranging from 0-10 mins. The UV source was a 230 watt UV lamp which was used with a filter so that it emitted UV light of a wavelength above 300nm. In the experiments detailed herein this lamp was held at a distance of approximately 1 foot from a sample to be irradiated. Exposure was through the Melinex layer, ie. this
20 layer was held facing the lamp.

- Thermal curing alone produced an adhesive with a reasonable peel strength. Low UV irradiation (for 1 or 2 minutes) did not have any apparent effect on the properties of the adhesive (peel strength
25 was assessed approximately by manually peeling the polyethylene sheet off the adhesive and noting how difficult it was to do this). Tackiness was assessed approximately by inserting a blunt object in the adhesive, rapidly withdrawing it and noting the tendency of the adhesive to prevent withdrawal of the object. However after 5
30 minutes irradiation a decrease in both peel strength and tackiness was apparent.

- Irradiation for 10 mins produced a very noticeable shrinkage of the adhesive (apparent after exposure of more than 5 mins
35 irradiation), resulting in slight curving and twisting of the laminated film. The adhesive itself peeled very easily and cleanly.

A film exposed for 2 mins to the UV light was removed from the polyethylene and irradiated for a further 2 mins so the adhesive was exposed to UV without it having passed through Melinex. This resulted in a large reduction in tack and also in peel strength. Cure times were approximately halved when the PSA was irradiated directly in this manner rather than through the Melinex.

b) Film 5b)

The same procedure was used as preparing the film 5a), except that Irgacure 784 (a visible light initiator) was used rather than Irgacure 651 (a UV initiator).

To 17.28g of the solution of Example 4, 0.0353g of AIBN and 0.0353g of Irgacure 784 were added and, after mixing, the liquid was spread to a depth of 0.010 inches on Melinex and left to dry at room temperature overnight in the dark.

c) Film 5c)

The same procedure was used as for preparing the film 5a) except that only thermal initiator (AIBN) was used.

To 17.33g of the solution of Example 4, 0.0355g of AIBN was added and, after mixing the liquid was spread to a depth of 0.010 inches on Melinex and left to dry at room temperature overnight in the dark.

A small sample of film 5c) was left on Melinex exposed to the light in a laboratory (some fluorescent light and some natural light through windows) over approximately 60 hours and this was found to have resulted in complete loss of tack.

A separate sample of film 5c) was thermally cured at 80°C for 15 mins and monitored when left at room temperature exposed to the light in a laboratory (fluorescent lighting as well as natural light coming through windows). The results obtained are summarised below in Table II:

TABLE II

Exposure Time	Properties of Adhesive
00 mins	good adhesive, good tack
03 mins	good adhesive, less tack
05 mins	poorer adhesive, much less tack
10 mins	poor adhesive, little tack
15 mins	poor adhesive, little tack
20 mins	poor adhesive, little tack
25 mins	poor adhesive, little tack
30 mins	poor adhesive, little tack
35 mins	poor adhesive, little tack

5 Complete loss of tack was not achieved after 24hrs, although tackiness was very low after this period.

A sample of film 5b) and film 5c) was left in a UV cabinet for 10 mins. After this irradiation time it was found that film 5b) cured more completely than film 5c).

10

d) Film 5d)

The same procedure was used as for film 5a) except that a photosensitiser was used instead of a photoinitiator. This was done in order to avoid the influence of free radicals produced by photoinitiation since it was believed that such free radicals were not necessary for detackification of the adhesive to occur. The photosensitiser used was Michler's Ketone.

20 To 37.26g of the solution of Example 4, 0.0758g of AIBN was added, as well as 0.0550g of Michler's Ketone. After mixing, a 0.010 inches film was spread on Melinex and left overnight at room temperature.

Example 6Peel Tests of Films 5a) and 5d)a) Film 5a)

- 5 Strips of film 5a) having a width of 25mm were applied to a polyethylene film of the type described above which has been first laminated to a steel plate to keep it flat. Light finger pressure, followed by two passes of a 2kg roller (width 1½", diameter 4") was used to laminate the film 5a) strips to the polyethylene film, with the
- 10 adhesive layer contacting the polyethylene film at its embossed surface (which mimics the surface of skin).

- The strips were allowed to remain laminated to the polyethylene film for 20 mins at 23°C in a 50% relative humidity
- 15 environment and were then peeled off the polyethylene at a rate of 300 mm/min along the length of the strips and using a 180°C peel as test described in British Pharmacopoeia Appendix XXH (Test 2). Some of the film 5a) samples laminated to the polyethylene were exposed to UV light for 15 mins of the said 20 mins (wavelength
- 20 greater than 300nm, frequency 50Hz) whereas others were left in the dark the whole time.

The results are illustrated in Table III:-

25

TABLE III

Sample	Peel Strength (N/m) without UV light	Peel Strength (N/m) with UV light
1	313)	33.5)
2	309.5) Average: 309	24) Average: 33
3	204.5)	38.5)

An average reduction in peel strength of 89% was thus obtained using UV curing.

30

b) Film 5d)

The procedure given for 5a above was repeated using film 5d) instead and the results obtained are illustrated in Table IV:-

TABLE IV

Sample	Peel Strength (N/m) without UV light	Peel Strength (N/m) with UV light
1	357.5))	35))
2	350.5) Average: 314.5	30.5) Average: 31.5
3	385.5)	29)

- 5 An average reduction in peel strength of 91% was thus obtained using UV curing, which is approximately the same as for film 5a).

10 Example 7 - Preparation of Polyurethane-anthracene
Adhesives

Polyurethane-anthracene switchable adhesives were prepared using the method of Example 4. The results are illustrated in Table V:-

TABLE V

Sample No.	PPG2025 Egvs OH	PEG600 Egvs OH	Ethanediol Egvs OH	Glycerol Egvs OH	NCO:OH	2-HEMA Egvs OH	Abitol Egvs OH	Anthracene Methanol Egvs OH
7a)	1.7	0.3	0.8	-	2.18	0.3	0.9	2.09
7b)	1.7	-	0.8	0.25	2.20	0.3	0.9	2.09
7c)	1.7	0.3	0.8	-	2.28	0.8	0.9	2.09

Example 8 - Peel Strength Tests

- Peel strength tests were carried out using the method of Example 2. The adhesives were peeled from a number of different substrates, steel, high density polyethylene (HDPE) and pig skin. Once laminated to the substrate the adhesives were either kept in the dark or irradiated under a UV source for a set time, always ensuring the same dwell time for both sets of adhesives. Changes in peel strength were therefore monitored by comparing the irradiated samples to the unirradiated control samples. The results are illustrated in Table VI:-

TABLE VI

<u>Sample No.</u>	<u>Substrate</u>	<u>Method of Film Preparation</u>	<u>Average Peel Strength (no UV cure) Nm⁻¹</u>	<u>Average Peel Strength (UV cured) Nm⁻¹</u>	<u>Irradiation time minutes</u>
7a i)	HDPE	Ex 5a)	618	66	15
7a ii)	HDPE	Ex 5d)	729	63	20
7b	HDPE	Ex 5d)	277	55	30
7c i)	HDPE	Ex 5c)	593	55	30
7c ii)	HDPE	Ex 5d)	579	28	30
7c iii)	Pig Skin	Ex 5d)	103	58	15

15

Example 9Preparation of Acrylate-anthracene Adhesives

- Acrylate adhesives were prepared as for Example 1 with the monomer mix as 6g acrylic acid, 47g butyl acrylate and 47g ethyl hexyl acrylate.

- The adhesive was converted to a switchable adhesive. The method used for esterification of the carboxylic acid groups pendant to the prepolymer chain employed a dehydrating agent, dicyclohexylcarbodiimide (DCC). This was used in conjunction with a dimethylaminopyridine catalyst with the reaction proceeding at room temperature. The following general procedure was initially used for the esterification reaction. For Example 9a), 6.09g of base PSA (containing 0.0068 moles acrylic acid) was placed in a dry jar along with 1.41g of anthracenemethanol (0.0068 moles), 1.39g DCC (0.0068 moles) and

30

24

- 0.33g DMAP (0.00027 moles). Approximately 100 ml of anhydrous tetrahydrofuran (THF) was added to the reaction mixture which was left stirring overnight (~ 24 hours). A precipitate was formed as a by-product of the esterification (dicyclohexylurea, DHU) which was insoluble in
- 5 THF and was therefore filtered from the PSA solution. A viscous yellow liquid was produced which was then spread thinly onto Melinex for UV irradiation.

- Further conversions were made and the results are shown in Table
- 10 VII:-

TABLE VII

Sample	No Moles of Acrylic Acid (in polymer)	No Moles of Anthracene Methanol	No Moles of DCC	No Moles of DMAP	Target AM Incorporation	Comments
9a)	0.0068 (6.09g polymer)	0.0068 (1.41g)	0.0068 (1.39g)	0.0027 (0.33g)	8%	Reaction at room temp for 24hrs in 100ml THF
9b)	0.0062 (5.58g)	0.0031 (0.64g)	0.0031 (0.63g)	0.0012 (0.15g)	4%	Reaction at room temp for 24hrs in 100ml THF
9c)	0.0048 (4.32g)	0.0011 (0.23g)	0.0011 (0.23g)	4.1×10^{-4} (0.05g)	2%	Repeat of 9c), reaction at room temp for 24hrs in 80ml THF

The anthracene methanol (AM) incorporation is illustrated in Table VIII:-

5

TABLE VIII

<u>Sample</u>	<u>Target AM Incorporation</u>	<u>Actual AM Incorporation</u>
9a)	8%	1.95%
9b)	4%	2.44%
9c)	2%	1.14%

The favoured approach for the esterification reaction was to react any excess acrylic acid (remaining from the reaction with anthracenemethanol) with methanol, this being added after the anthracenemethanol had reacted.

10

The switching results are illustrated in Table IX:-

15

TABLE IX

<u>Sample</u>	<u>% Incorporated AM in PSA</u>	<u>Irradiation Time</u>	<u>Result</u>
9a)	1.95	12 mins	low-tack film
9a)	1.95	20 mins	non-tacky film
9a)	1.95	45 mins	hard, non-tacky film
9b)	2.44	30 mins	non-tacky film
9c)	1.14	30 mins	low-tack film
9c)	1.14	1 hr	non-tacky film

Example 10Preparation of Acrylate Switchable Adhesives

20

Acrylate adhesives were prepared using ethyl hexylacrylate (EHA), butyl acrylate (BA) and acrylic acid (AA) were prepared using the method of Example 1.

The switchable adhesives were mixed with Irgacure photoinitiator. Samples were spread onto Melinex film. The samples were spread in an enclosed fume cupboard (darkened) and kept in a blacked out environment.

Adhesion to HDPE film, was based on the test described in the British Pharmacopiea (1988), Appendix XX, method H - adhesives test 2., except that: Peeling was after 30 minutes. The specimens were cut and laminated to the HDPE film coated steel plates in the dark, under a red safelight and either were kept in the dark until peeling or were exposed to light. Samples were transported and kept in light proof boxes until actual peeling.

The results are illustrated in the following Tables in which peel strength tests were carried out using:

halogen lamp (Table XI)
ambient light (Table X)
UV light (Table XI)

TABLE IX

Reductions in peel strength when irradiated with halogen lamp (1 foot from sample):

Estenified PSA	%EHA	%BA	%AA	%HEMA Incorp.	% Irradiance 784	Irradiation time (mins)	Mass Weight (gsm)	Peel Strength No Irradn. (N/m)	Peel Strength Irradiated (N/m)
10a)	44	44	7.27	4.73	10	15	34	180	13
					10	2	34	180	21
					10	15	23	140	10
					10	5	23	140	15
					10	2	23	140	20
10b)	45	45	5.83	4.17	10	15	38	300	25
					10	2	38	300	47
					10	15	37	300	20
					10	5	37	300	25
					10	2	37	300	50
10c)	47	47	2.92	3.08	10	15	32	348	53
					10	15	39	280	35
					5	5	39	280	45
					2	2	39	280	60
					1	1	39	280	120
					5	15	30	277	55
					2	5	30	277	63
					2	2	30	277	77
					2	15	28	265	59
					2	5	28	265	102
					2	2	28	265	110

Esterified PSA	%EHA	%BA	%AA	%HEMA Incorp.	% Inacure 784	Irradiation time (mins)	Mass Weight (gsm)	Peel Strength	
								No Irradn. (N/m)	Irradiated (Nm)
10d)	48	48	7.18	0.84	10	15	30	140	19
					10	5	30	200	30
						2	30	200	32
					5	15	28	120	23
					5	15	32	200	33
						5	32	200	47
					2	2	32	200	75
					2	15	31	180	51
						5	31	180	84
						2	31	190	140
	45	45	4.31	5.89	10	15	38	300	19
					5	15	38	337	22
					5	15	40	260	30
10f)	44	44	7.18	4.82	10	15	23	80	15
						5	23	80	12
						2	23	80	12
					5	15	22	91	15
						5	22	91	12
					2	2	22	91	15
					2	15	22	84	15
						5	22	84	15
						2	22	84	14
						2	22	84	14
						2	22	84	14
						2	22	84	14
						2	22	84	14

Esterified PSA	%EHA	%BA	%AA	%HEMA Incorp.	% Imacure 784	Irradiation time (mins)	Mass Weight (gsm)	Peel Strength	
								No Irradn. (N/m)	Peel Strength Irradiated (N/m)
10g)	47	47	3.0	3.0	10	15	27	100	15
						5	27	100	20
						2	27	100	20
						15	21	85	20
						5	21	85	20
						2	21	85	20
						15	21	80	25
						5	21	80	25
						2	21	80	25
						15	20	130	30
10h)	45	45	6.62	3.38	5	5	20	130	30
						2	20	130	40
						1	20	130	45
						15	34	200	40
						5	34	200	60
						2	34	200	80
						2	34	200	80

<u>Esterified</u> <u>PSA</u>	<u>%EHA</u>	<u>%BA</u>	<u>%AA</u>	<u>%HEMA</u> <u>Incorp.</u>	<u>% Imacure</u> <u>784</u>	<u>Irradiation</u> <u>time (mins)</u>	<u>Mass Weight</u> <u>(gsm)</u>	<u>Peel Strength</u> <u>No Irradn. (N/m)</u>	<u>Peel Strength</u> <u>Irradiated (Nm)</u>
10i)	46	46	4.92	3.08	10	15	26	65	15
						5	26	65	15
						2	26	65	20
						1	26	65	25
						15	26	65	15
						5	26	65	15
						2	26	65	20
						1	26	65	30
						15	26	100	20
						5	26	100	20
						2	26	100	20
						1	26	100	30
						15	26	120	20
						5	26	120	25
10j)	46	46	5.03	2.97	5	2	26	120	30
						1	26	120	55
						15	25	110	30
						5	25	110	35
						2	25	110	45
						1	25	110	55
						1	25	110	55

TABLE X

Reductions in peel strength when irradiated with ambient light

Estenified PSA	%EHA	%BA	%AA	%HEMA Incorp.	% Irracure 784	Irradiation time (mins)	Mass Weight (gsm)	Peel Strength No Irradn. (N/m)	Peel Strength Irradiated (Nm)
10k)	48	48	7.16	0.84	10	15	30	140	28
						30	30	140	17
					5	120	30	140	13
						15	28	120	28
						30	28	120	30
						120	28	120	21
10l)	45	45	4.31	5.69	10	15	38	300	72
						30	38	300	31
					5	120	38	300	18
						15	39	337	52
						30	39	337	38
						120	39	337	22

Example 12Acrylic PSA cross-linked with acrylate

- 5 111g toluene was refluxed at 70°C under nitrogen for 20 mins.
To this was added 0.0718 of bis(4-t-butylcyclohexyl)-peroxy
carbonate initiator (BCHPC) and then a monomer mixture of 46g
ethyl hexyl acrylate, 46g butyl acrylate, 8g itaconic anhydride was
added over 1.5 hours to the reaction vessel. A further 30g toluene
10 was added to the reaction after the monomer addition and then left
for 1.5 hours. A solution of 0.4482g BCHPC in 40ml toluene was
then added to the reaction in 10ml aliquots every 30 mins. The
reaction was then left stirring under nitrogen for 4 hours after a
further 126g toluene had been added. Note 1% by weight of
15 Irganox 1010 may be added to the PSA if required. The PSA
produced above was then reacted with 2-hydroxyethyl methacrylate
(equimolar quantity with regard to itaconic anhydride) in the
presence of catalytic quantity of sulphuric acid at ~50°C. This
reaction was complete in 10 hours to give a PSA with pendant
20 methacrylate groups. This reaction can also be carried out with
HEMA and itaconic anhydride interchanged.

- The switchable PSA was blended with 2% and 5% Irgacure
784 by weight and spread onto Melinex at 39gm⁻² and 50gm⁻²
25 respectively. Once dried the PSA was peeled from HDPE film both
before and after 15 mins irradiation from a visible light lamp.

The results are illustrated in Table XII:-

30

TABLE XII

<u>Irgacure 784</u>	<u>Peel Strength before irradiation</u>	<u>Peel Strength after irradiation</u>
2%	208 Nm ⁻¹	46Nm ⁻¹
5%	287 Nm ⁻¹	14Nm ⁻¹

Example 13

5 The reaction was carried out as for Example 12 except that itaconic anhydride was replaced with 3-isopropenyl- α,α -dimethyl benzyl isocyanate (m-TMI) in a solvent selected from toluene, acetone or ethyl acetate.

10 The base PSA was converted to a switchable PSA by reacting the base PSA containing m-TMI with 2-hydroxyl ethyl methacrylate (equimolar quantity with regard to m-TMI) in the presence of 1% (by wt of m-TMI) of dibutyl tin dilaurate catalyst. This reaction was carried out at 50°C for 8 hours.

15 The switchable adhesive was spread as for Example 12 with 2 and 5% Irgacure 784 by wt of switchable adhesive. The results are illustrated in Table XIII:-

TABLE XIII

20

<u>Irgacure 784</u> <u>Content</u> <u>%</u>	<u>Spread</u> <u>gm⁻²</u>	<u>Peel strength before</u> <u>irradiation</u> <u>Nm⁻¹</u>	<u>Peel strength after</u> <u>15 mins visible</u> <u>light irradiation</u> <u>Nm⁻¹</u>
5	31	255	23
2	30	208	28

CLAIMS

1. A switchable adhesive composition comprising an adhesive polymeric moiety and a plurality of bound-in curable moieties.
- 5 2. A switchable adhesive composition according to claim 1 wherein the adhesive polymeric moiety comprises an acrylate adhesive.
- 10 3. A switchable adhesive composition according to claim 2 wherein the acrylate adhesive is an acrylate copolymer.
4. A switchable adhesive composition according to claim 3 wherein the acrylate copolymer is an alkyl acrylate/alkyl
- 15 acrylate/acrylic acid tri-copolymer.
5. A switchable adhesive composition according to claim 4 wherein the acrylate copolymer is an n-butyl acrylate/2-ethylhexyl acrylate/acrylic acid tri-copolymer.
- 20 6. A switchable adhesive composition according to claim 1 wherein the bound-in curable groups are selected from acrylates, methacrylates and anthracenes.
- 25 7. A switchable adhesive according to claim 1 wherein the bound-in curable groups are free radical curable groups.
8. A switchable adhesive composition according to claim 1 wherein the amount present of bound-in curable moiety is from 0.4
- 30 to 50% by weight of polymer backbone.
9. A switchable adhesive composition according to claim 1 which includes a photoinitiator.
- 35 10. A switchable adhesive composition according to claim 1 in which the bound-in curable moiety is visible light curable.

11. A switchable adhesive composition according to claim 1 in admixture with an adhesive composition.
12. A process for the manufacture of a switchable adhesive composition according to claim 1 which comprises reacting an adhesive polymeric moiety with a curable moiety.
13. The use of a switchable adhesive composition according to claim 1 in the manufacture of an adhesive dressing.
14. An adhesive medical dressing comprising a backing layer substantially coated on at least one surface thereof with an adhesive according to claim 1.
15. 15. An adhesive medical dressing according to claim 14 wherein the backing layer comprises a light occlusive layer and a transparent or translucent layer.
16. An adhesive medical dressing comprising a backing layer and an adhesive layer wherein the backing layer comprises a removable light occlusive layer and a transparent or translucent layer intermediate the adhesive layer and the light occlusive layer and wherein the adhesive layer comprises an adhesive according to claim 1.
17. A method of treating a wound on a patient which comprises applying a dressing according to claims 14 or 16 to the wound of a patient.
18. A switchable adhesive composition as hereinbefore described.
19. An adhesive medical dressing comprising a switchable adhesive composition as hereinbefore described with reference to and as illustrated in the accompanying drawings.

1/1

FIG. 1.




FIG. 2.

